

PURE RESIN PA202

- REF. RA360;
- Nitrate Selective Resin
- macroporous strong base anion exchange resin supplied in the chloride form as moist, tough, spherical beads, specially designed for the removal of nitrates from water for potable processes;
- the macroporous matrix and special ion exchange group functionality imparts ideal nitrate selectivity to Pure PA202 making this resin particularly suitable for nitrate removal even when moderate to high sulphate concentrations are present.



Typical Physical & Chemical Characteristics	
Polymer Matrix Structure	Macroporous, Styrene with DVB
Functional Group	$R-N-R_3^+ Cl^-$
Ionic Form, as shipped	Cl^-
Physical Form and Appearance	Clear Spherical Beads
Sphericity	95% min.
Screen Size Range US Standard Screen	16 ÷ 50 mesh, wet
Particle Size Range	+1,2 mm < 5%, - 0,3 mm < 1%
Uniformity Coefficient	1,6 max.
Water Retention, Cl^- form	52 ÷ 56%
Shipping Weight	680 ÷ 730 g/l (42 ÷ 45,5 lbs/cu.ft, approx.)
Total Exchange Capacity	1,0 eq/l min.
Max Operating Temperature	100°C (212°F) max.
pH Range	0 ÷ 14

PURE RESIN PA202

Suggested Operating Conditions	
Maximum Operating Temperature	100°C (212°F) max.
Working Exchange Capacity @ 25°C	≥ 0,3 meq/l (wet)
Concentration of Regenerate Solution	NaCl: 8 ÷ 10%
Consumption of Regenerate	NaCl (8 ÷ 10%) Vol. : Resin Vol. = 2÷3 : 1
Flow Rate of Regenerate Solution	4 ÷ 6 (m/hr)
Regenerate Contact time	30 ÷ 60 (minute)
Rinse Flow Rate	15 ÷ 25 (m/hr)
Rinse Time (minute)	25 (approx.)
Operating Flow Rate	15 ÷ 25(m/hr)